
CALIFORNIA TECHNICAL BULLETIN 116

Norix Group, Inc
Bill Heinzerling
One Innovation Drive
West Chicago, IL 60185

Tested By:
Gavin D. Ray
Certified by:
Brent L. Larson

It is our policy to retain components and sample remnants for a minimum of 2 days from the report date, after which time they may be discarded. NOTE: all full scale flammability samples are discarded upon completion of the testing. The data herein represents only the item(s) tested. This report shall not be reproduced, except in full, without prior permission of Element Materials Technology.

Unless otherwise specified, measurement uncertainty was not taken into account when making statements of conformity to a specification.

EAR Controlled Data: This document contains technical data whose export and re-export/retransfer is subject to control by the U.S. Department of Commerce under the Export Administration Act and the Export Administration Regulations. The Department of Commerce's prior written approval is required for the export or re-export/retransfer of such technical data to any foreign person, foreign entity or foreign organization whether in the United States or abroad.

This project shall be governed exclusively by the General Terms and Conditions of Sale and Performance of Testing Services by Element Materials Technology. In no event shall Element Materials Technology be liable for any consequential, special or indirect loss or any damages above the cost of the work.

Sample ID: ARC250-XXX

California Technical Bulletin 116

INTRODUCTION:

This report documents testing conducted in accordance with California Technical Bulletin 116 (CA TB 116).

SUMMARY OF RESULTS:

The sample [MET](#) the test criteria of CA TB 116.

TEST METHOD:

Flammability testing was conducted in accordance with California Technical Bulletin 116, "Requirements, Test Procedure and Apparatus for Testing the Flame Retardance of Upholstered Furniture," January 1980. All furniture products and test materials were conditioned for a minimum of 48 hours at 65 - 80° F and <55% relative humidity.

TEST CRITERION (CA TB 116):

Test until either (a) three cigarettes have burned their full length, (b) three cigarettes have extinguished before burning their full length, or (c) one or more cigarettes have resulted in a failure per the method.

Individual cigarette test locations pass the test if the char length is not more than 2 inches in any direction from the nearest point of the cigarette.

EQUIPMENT AND MATERIALS:

Item	ID Number	Calibration Due Date
T/H Recorder	PT-161-124	06-08-24
Linear Scale(s)	PT-161-138	06-30-24
Cigarette	NIST 1196a	N/A
Sheeting	Testfabrics UF-400	N/A

TEST DATA:

See data sheet below.

Sample ID: ARC250-XXX


TEST RESULTS:

Date of testing: March 17th, 2024
Test room conditions at time of test: 72 °F and 50% RH
Sample Dimensions (L x W x H): 20" x 20" x 23 1/2"

Cigarette Number (P = Pass) (F = Fail) (R = Relight) (SE = Self Extinguished)				Number of Relights
Surface Type	1	2	3	
Top Surface	SE	SE	SE	0
Top Shelf	SE	SE	R	1
Bottom Shelf	SE	R	R	2

TEST RESULTS: The submitted sample **MET** the test criteria.

I certify that this test was carried out in accordance with the provisions of the CA TB 116 method.

Tested by:**Gavin D. Ray****Certified by:****Brent L. Larson**

Sample ID: ARC250-XXX