

# NORIX GROUP INC

## TEST REPORT

### SCOPE OF WORK

CALIFORNIA BUREAU OF HOME FURNISHINGS TECHNICAL BULLETIN 133 - JANUARY 1991,  
FLAMMABILITY TEST PROCEDURE FOR SEATING FURNITURE FOR USE IN PUBLIC  
OCCUPANCIES ON ATTENDA SPACE SAVER DESK – SMU293-XXX

### REPORT NUMBER

106222345SAT-001F

### TEST DATE(S)

06/11/2025

### ISSUE DATE


06/13/2025

### PAGES

8

### DOCUMENT CONTROL NUMBER

GFT-OP-10C (10/03/23)



## TEST REPORT FOR NORIX GROUP INC

Report No.: 106222345SAT-001F

Date: 06/13/2025

### REPORT ISSUED TO

#### NORIX GROUP INC

1 Innovation Drive

West Chicago, IL 60185

### SECTION 1

#### SCOPE

Intertek Building & Construction (B&C) was contracted by NORIX GROUP INC to perform testing in accordance with California Bureau of Home Furnishings Technical Bulletin 133 - January 1991 Flammability Test Procedure for Seating Furniture for Use in Public Occupancies, on their ATTENDA SPACE SAVER DESK – SMU293-XXX. This test determines peak heat release rate, mass loss and total heat release under an open furniture calorimeter. Weight loss was recorded as required by ASTM E1537 but not required by CATB 133. The ASTM E1537 is considered equivalent in respect to the testing procedures but not the test criteria. Results obtained are tested values and were secured by using the designated test method. The test was conducted at Intertek B&C test facility in Elmendorf, Texas.

Results obtained are tested values and were secured by using the designated test method. Testing was conducted at Intertek B&C test facility in Elmendorf, Texas.



Unless differently required, Intertek reports apply the "Simple Acceptance" rule also called "Shared Risk approach," of ILAC-G8:09/2019, Guidelines on Decision Rules and Statements of Conformity.

### SECTION 2

#### SUMMARY OF TEST RESULTS

ITEMS: Category B (Furniture Calorimeter)	READINGS	LIMITS	RESULTS
Maximum Rate of Heat Release (kW)	21	80	MET
Total Heat Release in 10 minutes (MJ)	1.84	25	MET
Weight Loss (lbs.) (Criteria for ASTM 1537)	0.01	3	MET

For INTERTEK B&C:

<b>COMPLETED BY:</b>	Theodore Salazar	<b>REVIEWED BY:</b>	Servando Romo
<b>TITLE:</b>	Technician 3	<b>TITLE:</b>	Dept. Manager
<b>SIGNATURE:</b>		<b>SIGNATURE:</b>	
<b>DATE:</b>	06/13/2025	<b>DATE:</b>	06/16/2025

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample(s) tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.