
Boston IX-11 Mattress Fire Test

Norix Group, Inc
Eddie Sot
1800 W. Hawthorne Lane – Suite N
West Chicago, IL 60185

Tested By:
Shane M. Lewis
Certified by:
Brent L. Larson

It is our policy to retain components and sample remnants for a minimum of 14 days from the report date, after which time they may be discarded. NOTE: all full scale flammability samples are discarded upon completion of the testing. The data herein represents only the item(s) tested. This certificate shall not be reproduced, except in full, without the written approval of the laboratory.

EAR Controlled Data: This document contains technical data whose export and re-export/retransfer is subject to control by the U.S. Department of Commerce under the Export Administration Act and the Export Administration Regulations. The Department of Commerce's prior written approval is required for the export or re-export/retransfer of such technical data to any foreign person, foreign entity or foreign organization whether in the United States or abroad.

This project shall be governed exclusively by the General Terms and Conditions of Sale and Performance of Testing Services by Element Materials Technology. In no event shall Element Materials Technology be liable for any consequential, special or indirect loss or any damages above the cost of the work.

Sample ID: MRB6-3680-C1NA-5F

OPEN FLAME EVALUATION – BOSTON IX-11

TEST RESULTS SUMMARY:

This report presents the results of a full scale **Boston IX-11** open flame test conducted on the following.

PROJECT #:	ESP029482P - Norix Group Inc
TEST SEQUENCE #:	2
TEST CONFIGURATION:	Test Room - 12' x 10' x 8'
PRODUCT MANUFACTURER or SUPPLIER:	Norix Group Inc
Sample ID:	MRB6-3680-C1NA-5F
TEST AREA: temp (°F) / R.H. (%): CONDITIONING ROOM: temp (°F) / R.H. (%): TIME OUT OF CONDITIONING (removal / test start - total):	68 / 50 69 / 33 07:30 PM / 07:38 PM - 8 minutes
TOTAL INITIAL MASS (kg):	13.55
TEST DATE:	10-05-2018
COMMENTS:	
Test Operator:	Shane Lewis / Jordan Nowak
Witness:	

Test Results	Data	Criteria	Pass/Fail
Peak rate of heat release (kW):	93.1	150 kW	--
Time @ peak release (mm:ss):	03 : 13	--	--
Total heat released @ 10 min (MJ):	18.9	30.0 MJ	--
Total mass loss @ 10 min (kg):	1.4	3.0 kg (6.6 lbs)	--
Total mass loss @ 30 min (kg):	2.9	3.0 kg (6.6 lbs)	--

PASS/FAIL CRITERIA:

PEAK RATE OF HEAT RELEASE SHALL NOT EXCEED 150 kW

TOTAL HEAT RELEASED AT 10 MINUTES SHALL NOT EXCEED 30 MJ

MASS LOSS SHALL NOT EXCEED THE WEIGHT OF THE BED CLOTHS

Sample ID: MRB6-3680-C1NA-5F

STANDARD TEST PROCEDURE:

This test was conducted in accordance with Boston Fire Department “BFD IX-11 Mattress Fire Test”. A brief summary is detailed below:

The mattress set was allowed to condition for at least 48 hours in conditions of: temperature – 70°F +/- 5° and relative humidity – less than 55. The instrumentation was calibrated and zeroed prior to the evaluation. The mattress set was placed on the bed frame and outfitted with the specified bed cloths prior to ignition. Data logging and video were obtained for 2 minutes prior to ignition.

The test proceeded until either all combustion had ceased, 30 minutes had passed or the development of a fire of such size as to require suppression for the safety of the facility.

NOTE: only heat release, total heat release and mass loss were reported.

Equipment		
Gas Analyzer	s/n: 653287	Calibration due date: 10-10-18
Dry Test Meter	s/n: 09L001965	Calibration due date: 02-16-19

REMARKS:

Due to the nature of the test, the specimen was discarded upon completion of the procedure.

Tested by:

Shane M. Lewis
Engineering Technician
Sleep System Evaluation

Certified by:

Brent L. Larson
Manager
Sleep System Evaluation
Phone: (651) 659 - 7218

Sample ID: MRB6-3680-C1NA-5F