
CALIFORNIA TECHNICAL BULLETIN 133 / ASTM E1537

Norix Group, Inc
Bill Heinzerling
One Innovation Drive
West Chicago, IL 60185

Tested By:
Noah B. Hitchen
Certified by:
Brent L. Larson

It is our policy to retain components and sample remnants for a minimum of 14 days from the report date, after which time they may be discarded. NOTE: all full scale flammability samples are discarded upon completion of the testing. The data herein represents only the item(s) tested. This certificate shall not be reproduced, except in full, without the written approval of the laboratory.

Unless otherwise specified, measurement uncertainty was not taken into account when making statements of conformity to a specification.

EAR Controlled Data: This document contains technical data whose export and re-export/retransfer is subject to control by the U.S. Department of Commerce under the Export Administration Act and the Export Administration Regulations. The Department of Commerce's prior written approval is required for the export or re-export/retransfer of such technical data to any foreign person, foreign entity or foreign organization whether in the United States or abroad.

This project shall be governed exclusively by the General Terms and Conditions of Sale and Performance of Testing Services by Element Materials Technology. In no event shall Element Materials Technology be liable for any consequential, special or indirect loss or any damages above the cost of the work.

Sample ID: 032-XB0XX

OPEN FLAME EVALUATION – CA T.B. 133 / ASTM E1537**TEST RESULTS SUMMARY:**

This report presents the results of a full scale open flame test conducted on the following.

PROJECT #:	ESP042839P - Norix Group Inc
TEST SEQUENCE #:	1
TEST CONFIGURATION:	Open HOOD
PRODUCT MANUFACTURER or SUPPLIER:	Norix Group, Inc.
Sample ID:	032-XB0XX
TEST AREA: temp (°F) / R.H. (%): CONDITIONING ROOM: temp (°F) / R.H. (%): TIME OUT OF CONDITIONING (removal / test start - total):	72 / 57 70 / 48 01:52 PM / 01:57 PM - 5 minutes
TOTAL INITIAL MASS (kg):	18.45
TEST DATE:	08-30-2024
COMMENTS:	
Test Operator:	Noah Hitchen
Witness:	

Test Results	Data	Criteria	Pass/Fail
Peak rate of heat release (kW):	20.3	80 kW	Pass
Time @ peak release (mm:ss):	00 : 52	--	--
Total heat released @ 10 min (MJ):	1.6	25.0 MJ	Pass
Total mass loss @ 10 min (kg):	0.0	1.4 kg (3.0 lbs)	Pass

PASS/FAIL CRITERIA (CA T.B. 133 only):

PEAK RATE OF HEAT RELEASE SHALL NOT EQUAL OR EXCEED 80 kW
TOTAL HEAT RELEASED AT 10 MINUTES SHALL NOT EQUAL OR EXCEED 25 MJ
MASS LOSS DUE TO COMBUSTION AT 10 MINUTES SHALL NOT EQUAL OR EXCEED 1.4 KG (3 LBS)

Sample ID: 032-XB0XX

STANDARD TEST PROCEDURE:

This test was conducted in accordance with California Technical Bulletin 133 / ASTM E1537, a brief summary is detailed below:

The sample was allowed to condition for at least 48 hours in conditions compliant with California technical bulletin 133 / ASTM E1537 (temperature – 70°F ± 5°F / relative humidity – less than 55%). The instrumentation was calibrated and zeroed prior to the evaluation. After the specimen was placed on the scale, the burner alignment procedure was performed. Data logging and video were obtained for 2 minutes prior to burner ignition. The burner application time was 80 seconds. Upon completion of the flame application time, the burner unit was removed from the test area.

The test proceeded until either all combustion had ceased, 60 minutes had passed or the development of a fire of such size as to require suppression for the safety of the facility.

Equipment		
Gas Analyzer	s/n: 200220	Calibrated Daily Prior to Use
Scale	s/n: 156911/C27927	Calibration due date: 6-6-2025

REVISION:

This report was updated with the addition of “ASTM E1537” to the test description.

REMARKS:

Due to the nature of the test, the specimen was discarded upon completion of the procedure.

Tested by:

Noah B. Hitchen
Engineering Technician
Sleep System Evaluation

Certified by:

Brent L. Larson
Manager
Sleep System Evaluation
Phone: (651) 659 - 7218



Sample ID: 032-XB0XX